

LACOR FLOATING FLOOR SPECIFICATIONS

TESTS	METHODOLOGY	UNIT	RESULTS
Fire Resistance	UNI 8457 UNI 9174	Class	1
<u>Abrasion</u> Resistance	Taber Test UNI 9115/87	Level from 1 to 5	5
Stain Resistance	EN 12720/97	Class from A to F	C
Resistance to boiling water	SSS 045 SGQ 04/2003-00	Presence/absence disaggregating agg.	Absent
Resistance to accelerated aging UV/Condense	ASTM G53 condensed exposure to UVB rays equal to 240 hours	Color variation of the Grigi scale	4 samples do not present dimensional distortions
Various dimension check	SSS 050 SGQ 04/2003-00 Treatment in a climatic cell for 10 days at 60 C relative humidity 65%	Value %	< 0,1%
Resistance to face parallel traction	SSS 038 SGQ 04/2003-00 jaw line distance 12 mm	Unitary weight Kg/cm ²	19,30

SPECIFICATIONS

Commercial denomination:	Lacor Floating Floor
Standard dimension:	305x305x4,8 mm

SOME OF THE PRODUCTION PHASES



Extraction



Recycling Matrial



Granulated



Blocks




Stabilization Tiles



Block Sectioning



Press Line



Finishing



Quality Control



Finished product